LEGOR®

MASTER ALLOY

TECHNICAL SHEET

OG130A 375‰

MASTER ALLOY FOR CASTING OF 375-585‰ (9-14 KT) YELLOW GOLD

GENERAL INFORMATION

General information	
Color	Yellow
Typology	Master alloy for gold
Color shade	Light yellow
Production process	Casting
Melting temperatures	
Liquidus [°C]	900.0
Solidus [°C]	820.0
Melting range [°C]	80.0

Commercial composition	
Silver (%)	12,00
Copper (%)	71,00
Zinc (%)	17,00



GOLD line

FULL CHARACTERIZATION DATA

Color coordinates	
L*	85.9
a*	1.8
b*	18.5
c*	18.6
General characteristics	
As cast grain size [µm]	485.0

Mechanical characteristics	
As cast hardness [HV 0.2]	100.0
Hardness after annealing [HV 0.2]	120.0
Hardness after 70% area red. [HV 0.2]	265.0
Tensile strength (Rm) [Mpa]	426.0
Yield strength (Rp0.2) [MPa]	216.0
Elongation at rupture (A) [%]	37.0

Product applications
Casting without stones
Casting in open systems

RELATED PRODUCTS LIST

Related Products	
LSG409	Master alloy for soldering of 585‰ (14 Kt) yellow gold
LSG409D	Master alloy for soldering of 585‰ (14 Kt) yellow gold
LSG417F	Master alloy for soldering of 375-585‰ (9-14 Kt) yellow gold
LSG419	Master alloy for soldering of 375‰ (9Kt) yellow gold
Alternative Products	
B145	Master alloy for mechanical working of 375-585‰ (9-14 Kt) yellow gold
C142GR	Master alloy for casting of 375-585‰ (9-14 Kt) yellow gold

Print Date 17/05/2019

LEGOR GROUP S.P.A. - Via del Lavoro, 1 - 36050 (VI) - Italy - Tel. +39 0444 467911 - Fax +39 0444 660677 - info@legor.com - www.legor.com

TECHNICAL SHEET

OG130A 375‰

MASTER ALLOY FOR CASTING OF 375-585‰ (9-14 KT) YELLOW GOLD

CASTING PROCESSING PARAMETERS

Pre-mixing temperature [°C]	1020.0

CASTING TEMPERATURES	Flask from [°C]	Flask to [°C]	Metal from [°C]	Metal to [°C]
< 0.5 mm	660.0	720.0	1000.0	1030.0
0.5 - 1.2 mm	580.0	650.0	980.0	1000.0
> 1.2 mm	460.0	600.0	960.0	980.0

Trees without stones

Let the flask cool down for 10-15 minutes, then quench in water.

Stone-in-place casting trees

Let the flask cool down for 30-45 minutes, then quench in water.

Pickling

Dip in RADIAL solution (50 g/l conc. at 60°C for 2 min.), or in sulphuric acid (10% conc. at 50°C for 5 min.)

Print Date 17/05/2019

LEGOR GROUP S.P.A. - Via del Lavoro, 1 - 36050 (VI) - Italy - Tel. +39 0444 467911 - Fax +39 0444 660677 - info@legor.com - www.legor.com